



A Division of California Products • An Employee Owned Company
150 Dascomb Road, Andover Massachusetts 01810 USA
Phone: 978-623-9980 / 800-225-1141 • Fax: 978-623-9960
www.plexipave.com • info@plexipave.com

SECTION 10.22

EXTERIOR/INTERIOR

**SITE IMPROVEMENTS
ATHLETIC FACILITIES**

PLEXICUSHION PATCH COMPOUND

DESCRIPTION:

Plexicushion Patch Compound is a ready-to-use single unit Latex patching and leveling compound designed to easily patch and fill shallow depressions in Plexicushion surfaces without the mixing of several components. It can be used to level birdbath areas quickly and easily. Plexicushion Patch Compound provides a resilient patch to meet the demands of resilient surfaces.

SURFACE USES:

For properly prepared asphalt and concrete surfaces. (See Specification 10.0 and 10.23).

- Tennis Courts
- Basketball Areas
- Play Areas
- All-Purpose Sports Areas
- Rooftop Recreation Areas

APPLICATION:

Depending on the size of the area to be patched or leveled, application is by hand trowel, squeegee, or screed. In most cases a cement finisher's trowel is necessary to smooth the surface. A damp mason's sponge may be used to feather the edges of the patched area.

DRYING TIME:

In thin patches up to 1/8", drying time will occur between 30 minutes and 1 hour in normal summer conditions.

COLOR RANGE:

Bluish/Black

COVERAGE:

One gallon of Plexicushion Patch Compound will cover 10 s.f. 1/8" thick.

LIMITATIONS:

- Apply only when ambient temperature is 60°F and rising.
- Do not apply Plexicushion Patch Compound when rain is imminent within 4 hours.
- Keep material from freezing.
- Do not store in the hot sun.
- Keep containers tightly closed when not in use.
- Do not apply when surface temperature is in excess of 140F.
- Do not apply in thickness greater than 1/2" in one lift.

**SPECIFICATIONS
PLEXICUSHION PATCH COMPOUND**

1.0 SURFACE PREPARATION

1.1 All surfaces to be repaired or leveled with Plexicushion Patch Compound shall be clean and free from loose dirt, dust, greases and oils. Any cracks should be blown clean with an air compressor. Surfaces shall be dry before application begins.

2.0 APPLICATIONS

2.1 All areas to be leveled and patched shall be outlined at the extent of the area to be covered. Plexicushion Patch Compound shall be laid in with a hand trowel, squeegee or screed depending on the size of the patch. Plexicushion Patch Compound shall be thoroughly mixed with a mechanical agitator prior to its application. After installation, a moist mason's sponge may be used to feather the edges so that no ridges will appear in subsequent coats of the Plexipave Color Finish System.

2.2 After drying, any rough edges shall be sanded smooth and loose material shall be carefully removed from the court or recreational area by air broom and/or sweeping.