



A Division of California Products • An Employee Owned Company  
150 Dascomb Road, Andover Massachusetts 01810 USA  
Phone: 978-623-9980 / 800-225-1141 • Fax: 978-623-9960  
www.plexipave.com • info@plexipave.com

## **SECTION 10.32**

EXTERIOR/INTERIOR

**SITE IMPROVEMENTS  
ATHLETIC FACILITIES**

### **PLEXIPAVE GRAND PRIX**

#### **DESCRIPTION:**

Plexipave Grand Prix is a unique 100% acrylic textured coating specifically formulated for use with the resilient Plexicushion substrate. The flexible acrylic binder used in Plexipave Grand Prix responds to the shock absorbing Plexicushion to enhance the full effect of the Plexicushion System.

Plexipave Grand Prix is textured and pigmented to withstand the deteriorating effects of foot traffic and harmful ultraviolet rays.

#### **SURFACE USES:**

Over Plexicushion and other approved resilient surfaces

- Tennis Courts
- Basketball Areas
- Play Areas

#### **APPLICATION:**

- 24" or 36" 50-durometer flexible rubber squeegees as approved by the Manufacturer.
- Refer to Plexicushion specification – for detailed installation instructions.

#### **DRYING TIME:**

- 30 minutes to one hour depending on ambient temperature and humidity. A three-coat application in normal summer drying weather can be made over a properly prepared court surface in one day.
- Indoor drying will be significantly longer. After the application of the final coat, allow 48 hours to cure before use.

#### **COLOR RANGE:**

- 9 selected color: Light Green, Dark Green, Florida Green, Sahara Sand, Pacific Blue, Cape Gray, Brown, Maroon, and Red.

#### **COVERAGE:**

(Depending on Surface Porosity)

- First Coat – 10-15 square yards per gallon (.1-.07 gall./sq.yd.)
- Second Coat – 15-20 square yards per gallon. (.07-.05 gal./sq. yd.)

- Third Coat – 20-25 square yards per gallon. (0.5-0.4 gal./sq. yd.)

**LIMITATIONS:**

- Apply only when ambient temperature is 50°F and rising.
- Keep containers tightly close when not in use.
- Do not apply when rain or high humidity is imminent.
- Do not apply when surface temperature is in excess of 140F.
- Allow asphalt to cure at least 14 days.
- Allow concrete to cure 28 days. Do not allow use of concrete curing agents or hardeners.
- Keep from freezing – Do not store in hot sun.
- The Plexipave System will not prevent pavement cracks from occurring.