

CP4170**TYPICAL PHYSICAL PROPERTIES:**

Emulsifiers	Anionic
Bound Styrene	65%
Viscosity (Brookfield #2, 20 rpm)	200 cps
Glass Transition Temp. (Tg)	-70° C
pH	9.0
Solids Content	50.0%
Particle Diameter	0.15 Microns
Residual Monomer	0.07% Max